

Capran® 524 is a blue-green tinted heat stabilized blown film produced from modified nylon resin. It is recommended as a bagging film for advanced composite fabrication and other high temperature applications where softness and workability are essential. Capran 524 has excellent heat stability and resistance to pin-holing. Capran 524 is available in sheet, tube and V-sheet in widths ranging from 48" to 80".

Product Specifications		
Thickness (ASTM D6988)		Yield (calculated)
Average	Single Point Minimum	
2.00 mils (50.8 microns) ± 12%	1.70 mils (43.2 microns)	12,234 in ² /lb (17.4 m ² /kg) ± 12%
3.00 mils (76.2 microns) ± 12%	2.55 mils (64.8 microns)	8,156 in ² /lb (11.6 m ² /kg) ± 12%

Properties at 73°F(23°C) - 50%RH	Typical Value		Test Method
	English	Metric	
The properties presented in this data table are typical values and are not to be interpreted as product specifications.			
Tensile Strength @ break	15,000 psi	103 MPa	ASTM D882
Elongation @ break	400%		ASTM D882
Modulus, Secant	80,000 psi	552 MPa	ASTM D882
Melting Point	406°F	208°C	DSC
Maximum Recommended Use Temperature ⁽¹⁾	375°F	190°C	-----

Capran 524, like all nylon films, is a hydrophilic or water-sensitive material. Moisture and water act as plasticizers. The higher the moisture content of the film, the more flexible it becomes. The lower the plasticizer content, the stiffer it becomes. The level of moisture content at time of use is an important factor for successful performance.

NOTE: (1) The maximum recommended use temperature is a function of the duration at maximum temperature and is process specific.

DISCLAIMER: Although Honeywell International Inc. believes that the values and information contained herein is accurate and reliable, it is not intended to be product specifications, and are presented without guarantee or responsibility of any kind and does not constitute any representation or warranty from Honeywell, whether express or implied. A number of factors can affect the selection and use of films. Nothing presented herein shall relieve the user from the responsibility of carrying out its own assessment, verification, and safety protocols. Any information and technical support provided by Honeywell is gratuitous in nature and offered without any warranties or representation. The user assumes all risks and liability for the use of the information contained herein, including, but not limited to, risks relating to results, patent infringement, regulatory compliance and health, safety and environment.

Capran is a registered trademark of Honeywell International Inc.

