## $f \Gamma\! ech \,\,$ AWTVF-HS Red (Capran $^{ ext{ iny B}}$ HS Red)

**Capran® HS Red** is a red tinted heat stabilized blown film produced from low lactam nylon 6 resin. It is recommended as a bagging film for advanced composite fabrication and other high temperature applications where softness and workability are essential. Capran HS Red has excellent heat stability and resistance to pin-holing. Capran HS Red is available in sheet, tube and V-sheet in widths ranging from 48" to 80".

Product Specifications				
Thickness (ASTM D6988)		Viold (polaulated)		
Average	Single Point Minimum	Yield (calculated)		
2.00 mils (50.8 microns) ± 12%	1.70 mils (43.2 microns)	12,224 in <sup>2</sup> /lb. (17.4 m <sup>2</sup> /kg) ± 12%		
3.00 mils (76.2 microns) ± 12%	2.55 mils (64.8 microns)	8,151 in <sup>2</sup> /lb. (11.6 m <sup>2</sup> /kg) ± 12%		

Dranartica	Typical Value			
Properties at 73°F(23°C) - 50%RH	English	Metric	Test Method	
The properties presented in this data table are typical values and are not to be interpreted as product specifications.				
Tensile Strength @ break	14,000 psi	96 MPa	ASTM D882	
Elongation @ break	415%		ASTM D882	
Modulus, Secant	80,000 psi	552 MPa	ASTM D882	
Melting Point	424°F	218°C	DSC	
Maximum Recommended Use Temperature (1)	400°F	204°C		

**Capran HS Red,** like all nylon films, is a hydrophilic or water-sensitive material. Moisture and water act as plasticizers. The higher the moisture content of the film, the more flexible it becomes. The lower the plasticizer content, the stiffer it becomes. The level of moisture content at time of use is an important factor for successful performance.

NOTE: (1) The maximum recommended use temperature is a function of the duration at maximum temperature and is process specific.

**DISCLAIMER:** Although Honeywell International Inc. believes that the values and information contained herein is accurate and reliable, it is not intended to be product specifications, and are presented without guarantee or responsibility of any kind and does not constitute any representation or warranty from Honeywell, whether express or implied. A number of factors can affect the selection and use of films. Nothing presented herein shall relieve the user from the responsibility of carrying out its own assessment, verification, and safety protocols. Any information and technical support provided by Honeywell is gratuitous in nature and offered without any warrantees or representation. The user assumes all risks and liability for the use of the information contained herein, including, but not limited to, risks relating to results, patent infringement, regulatory compliance and health, safety and environment.

Capran is a registered trademark of Honeywell International Inc.



PH: +1 817 438 4777 / FAX: +1 940 294 1429 ADDRESS: 2411 E. FM917 # 200 Mansfield, TX 76063 – USA EMAIL: sales@aerowindtech.com